

KLEIBERIT 657.0.36

UV-curing roller top coating, super matt, colour 036, for KLEIBERIT HotCoating®

Fields of Use

- Photosensitive UV top coat for the KLEIBERIT HotCoating® technology in colour 036 and a gloss level of < 5 units.

Characteristics of 657.0.36

Base:	UV curing acrylates
Specific weight (at 20 °C):	approx. 1,22 g/cm ³
Solids:	>99% (theoretical value)
Colour:	036
Gloss level 60°:	< 5 units The gloss level depends on the processing parameters.

Viscosity at delivery (at 20 °C)

6mm DIN cup: 25 - 35 seconds

Identification: See our safety data sheet

Processing

Ambient and substrate processing temperature: 22 - 28 °C
 Application with roller applicator: 25 - 45 g/m²
 Application viscosity: viscosity at delivery

Stir well before use.

All process relevant properties must be checked before processing.

Drying/UV-Curing

Precuring:	excimer
Curing:	10 m/min
UV-Dosis*:	880 - 930 mJ/cm ² (Hg) and
UV-Dosis*:	350 - 400 mJ/cm ² (Ga)

* The stated UV doses are empirical values based on measurements with „UV-Disc A002400 (Full-UV: 250 – 410 nm)“ by UV-Technique.

It is crucial to determine the processing conditions for optimal results before starting production.

These depend on the systems technology as well as on the substrate to be coated.

The final properties like adhesion, scratch resistance and sanding properties have to be monitored continuously.

Cleaning

Soiled application tools and machinery parts to be cleaned immediately with KLEIBERIT 820.0.

Packaging

KLEIBERIT 657.0.36 UV TopCoat

metal pail, 30 kg net

Cleaner

KLEIBERIT 820.0

metal can, 22 kg net

Additional packaging sizes available upon request.

Storage

Shelf life in factory sealed containers (at 5 - 25°C) is at least 12 months.

Storage at high temperatures can shorten the shelf life.

Recommended transport temperature:

-10 °C to 35 °C

The product is not frost sensitive to 0 °C.

Protect from light and heat.

Version 19.06.2024 xv; replaces previous versions